



Euromix™ Euroflex is a high solids, acrylic based waterproofing and decorative paint coating that provides excellent flexibility, elasticity and durability on surfaces subjected to high winds, salt spray and severe weather conditions.

1. Product Summary:

As well as providing the colour for wall or ceiling finishes, Euromix Primers and Paints add to the functionality of the finish system. They have been chosen on the basis of their ability to enhance the appearance and serviceability of our renders, textures and plasters.

Euromix Euroflex is most often used as the final coloured topcoat over render and texture coated surfaces to provide an effective waterproofing barrier that also breathes – allowing vapor to escape from the substrate. Substrates must be primed with Euromix Acrylic Primer prior to the application of the Euroflex.

White in colour at the time of manufacture, Euromix Euroflex can be pigmented (tinted) to achieve a desired colour.

Product Name	Euromix® Euroflex
Code	FLEXWB15
Packaging	15 litre plastic buckets.
Appearance	In the bucket the material appears as a wet, off-white, thick liquid.

2. Product Features:

Applicators appreciate the ease of application that results from the inclusion of selected workability chemicals.

Euroflex is touch dry in 1 hour and fully cured within 24 hours, depending on weather.

Euroflex is designed to deliver long lasting protection and aesthetics. Special polymers ensure that it resists dirt and is easily washed, while also giving high tensile strength characteristics that mean it can bridge minor cracking.

When used as a final coat the hard satin finish is resistant to the accumulation of dust and dirt. Sealer Primer can also be used as waterproofing barrier in most decorative walling applications.

3. Typical Uses:

Euroflex is suitable for coating most suitably prepared building substrates, including; off-form concrete, cement render fibre cement sheeting, brick and block work.

Surface imperfections must be fixed prior to applying the Euromix Euroflex to achieve the desired finish. Substrates and or joints may need to be prepared with Euromix™ Patch or one of the Euromix™ Renders.



Euromix™ Euroflex is the recommended final coat for Euromix Texture finishes.

4. General Performance Guidelines:

Weather	Excellent resistance to cracking & chalking
Water	Good water resistance.
Temperature	Suitable for walls exposed to temperatures up to 60C dry.
Abrasion	Good resistance, but not suitable as a coating in high traffic thoroughfares.
Solvents	Sensitive to strong solvents

5. Application Guidelines:

5.1 Surface Preparation:

Ensure that alkaline surfaces have aged for twenty-eight (28) days minimum.

Surfaces must be sound, stable, dry, clean and free of dust, loose, flaking, friable material and substances that may diminish adhesion.

Mask windows and architectural trim elements before applying Texture. Floor and adjacent walling materials should be protected against spills and splashes by plastic film or similar.

Surface imperfections should be repaired prior to coating to achieve a good result and desired finish. Cracks should be filled with a suitable filler and finished flush with the surface in accordance with good painting practice.

Australian Standard AS 2311 (The Painting of Buildings) sets out acceptable standards which the applicator must be satisfied have been met.

Priming of surfaces can be achieved by applying Euromix Sealer Primer (solvent base) or Euromix Acrylic Primer, depending on the nature of the substrate, the prevailing site conditions and the type of finish desired.

Euromix Sealer Primer is a solvent base based penetrative primer that is applied without tinting while the Acrylic Primer can be tinted to match the Euroflex.

Allow four (4) hours in normal conditions, for the Euromix Sealer primer or the Euromix Primer to dry before applying the Euroflex.

5.2 Application

It is recommended that the Euroflex be thoroughly stirred in the bucket, using a power stirrer, prior to application.

The Euroflex can be applied by brush, roller or spray in a minimum of two coats (if applying by roller it is recommended that a 6-8 mm nap roller sleeve be used) at the rate of 1.5 SQM / Litre per coat.

Allow a minimum six (6) hours drying between coats.

It is imperative that a 'wet-edge' is maintained at all time. Ensure that there are sufficient operators available on large areas.

Do not apply Euromix Paints and Textures in windy conditions or in temperatures outside the range 10C to 30C. Keep newly coated areas protected from rain and moisture for at least twelve (12) hours, longer in the lower temperature range.

Direct exposure to rain is not the only issue - run-off or wind driven moisture can also cause coating failure!

5.3 Coverage:

Average approximate spread rate for Euromix Euroflex is 25 to 30 SQM per 15 litre bucket. This will vary depending upon type, condition and porosity of the substrate, application technique and the tinted colour.

5.4 Drying and Curing

Drying and curing of the product is affected by type, dryness and porosity of the surface, temperature, humidity, ventilation, climate conditions and application technique and therefore drying and curing can only be given as a guide (at 25C & 50% RH):

Touch Dry	Two (2) to four (4) hours.
Recoat	Six (6) hours.

5.5 Clean Up:

Clean up with water. Do not let material enter drains.

If spilled, use sand to cover the wet material and then dispose of in accordance with the local regulations.

Clean tools, with solvent before product sets.

6. Limitations in Use:

Do not apply in temperatures outside the range 10C to 30C.

The material should not be subjected to hydrostatic pressure, continual or excessive rising damp.

Euromix recommends that Euromix Euroflex be applied by experienced building contractors and trades people.

Do not apply if rain or frost is imminent or possible before the product has properly dried. Painting over wet or damp substrates will most often result in some form of failure, including possible discolouration and / or colour variation and peeling.

Euromix will not accept responsibility for misuse of this product.

7. Health & Safety:

For full safety data refer to the product's Material Safety Data Sheet. The following information is a guide only:

Precautions in Use	The use of gloves and goggles is recommended as the product may irritate skin and eyes.
Safety & Precautions	If product gets into the eyes, flush with thoroughly with clean water. If on skin, remove contaminated clothing and wash with soap and water. Do not use solvent. If inhaled (an unlikely event due to the viscosity of the product) remove person to fresh air and apply artificial respiration if required..

8. Handling, Storage & Transport:

Handling	Euromix Sealer Primer is supplied in 15 litre metal drums - recognised local safe lifting methods should be used.
Storage	Store in a cool / dry area that is protected from excessive heat, frost, moisture and possible container damage. Do not let product freeze.
Shelf Life	Approximately 12 months in unopened containers.

The information contained in this product data sheet is typical and does not constitute a full specification, as conditions will vary from project to project.

All purchasers and intending users of the products covered in this document must, prior to use, assess and control the risks arising from use of the products, as they relate to their project.

For further information please contact Euromix, via the contact details listed below;

Supplier	Euromix Pty Ltd ABN 57664946070
Address	31-33 Water Street Strathfield South NSW 2136
Telephone	(02) 9572 9061
Email	contact@euromix.com.au